

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 June 2003 (05.06.2003)

PCT

(10) International Publication Number
WO 03/045618 A1

(51) International Patent Classification⁷: **B23K 35/00,**
35/02

Evanston, IL 60201 (US). **CHEADLE, Brian, E.**
[CA/CA]; 71 Ashwood Crescent, Bramalea, Ontario L6T
1M1 (CA).

(21) International Application Number: PCT/CA02/01762

(74) Agent: **JOACHIM, Roland, H.**; Ridout & Maybee LLP,
One Queen Street East, Suite 2400, Toronto, Ontario M5C
3B1 (CA).

(22) International Filing Date:
21 November 2002 (21.11.2002)

(25) Filing Language: English

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.

(26) Publication Language: English

(30) Priority Data:
09/990,507 21 November 2001 (21.11.2001) US

(63) Related by continuation (CON) or continuation-in-part
(CIP) to earlier application:
US 09/990,507 (CIP)
Filed on 21 November 2001 (21.11.2001)

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **DANA
CANADA CORPORATION** [CA/CA]; 656 Kerr Street,
Oakville, Ontario L6K 3E4 (CA).

(71) Applicant (*for US only*): **HOFFMAN, Margaret, Anna**
(legal representative of the deceased inventor) [US/US];
5061 Sequoia Court, Esport, PA 15632 (US).

Published:
— with international search report
— before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(72) Inventor: **HOFFMAN, Richard, A.** (deceased).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **GRAHAM,
Michael, E.** [US/US]; 2430 Central Park Avenue,

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: FLUXLESS BRAZING METHOD AND COMPOSITIONS OF LAYERED MATERIAL SYSTEMS FOR BRAZING
ALUMINUM OR DISSIMILAR METALS

(57) Abstract: A brazing product for fluxless brazing comprises an aluminum or aluminum alloy substrate; a layer of an aluminum eutectic-forming layer applied to the substrate, and a braze-promoting layer comprising one or more metals from the group comprising nickel, cobalt and iron is applied on the eutectic-forming layer. The eutectic-forming layer is preferably Si deposited by physical vapor deposition. The brazing product may be brazed to another aluminum shape or to a shape comprised of a dissimilar metal.



WO 03/045618 A1

FLUXLESS BRAZING METHOD AND COMPOSITIONS OF LAYERED MATERIAL SYSTEMS FOR BRAZING ALUMINUM OR DISSIMILAR METALS

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This is a continuation-in-part of U.S. Patent Application No. 09/990,507, filed November 21, 2001, now pending, incorporated herein by reference.

FIELD OF THE INVENTION

[0002] The invention addresses the objective of achieving a cladless brazing material system, while maintaining a fluxless brazing system.

BACKGROUND OF THE INVENTION

[0003] Brazing commonly involves the use of aluminum-silicon clad aluminum brazing sheet composites. Because sophisticated rolling mill practices are required to produce this traditional composite, a premium cost is involved over conventional flat rolled sheet and strip. Also, available alloy compositions are limited by mill product standardization, by casting limitations, or by scrap recovery considerations that affect the economy of the overall casting or mill operation.

[0004] Such conventional brazing alloys can be brazed using fluxless brazing systems, which typically use an electroplated braze-promoting layer. However, there are environmental hazards and liabilities associated with prior art wet electroplating systems for deposition of fluxless braze modifiers. Furthermore, there are limitations on the range of material strip or component dimensions which can be electroplated in high volume production, for example the constraints of fixed size plating cells limit the maximum plateable strip width.

SUMMARY OF THE INVENTION

[0005] In one aspect, the invention provides a method for manufacturing an

article of manufacture for use in a fluxless brazing process, comprising: (a) providing a metal substrate; (b) applying to the substrate a eutectic-forming layer comprising a material which forms a eutectic with the metal substrate; and (c) applying to the eutectic-forming layer a braze-promoting layer comprising one or more metals selected from the group comprising nickel, cobalt and iron.

In another aspect, the invention provides a method of brazing unclad first and second aluminum alloy shapes, at least one of the alloy shapes comprising a metal substrate, a layer of a eutectic-forming material applied to the substrate, and a layer of a braze-promoting layer on the eutectic forming material, the method comprising: (a) assembling the shapes into an assembly to create contact between the shapes; (b) heating the assembly under a vacuum or in an inert atmosphere in the absence of a brazing flux material at an elevated temperature and for a time sufficient for formation of a molten filler metal comprising a eutectic of said metal substrate and the eutectic forming material, and melting and spreading of the molten filler metal to form a joint between the shapes; and (c) cooling of the joined assembly.

[0006] In yet another aspect, the invention provides a brazing product for fluxless brazing, comprising: (a) a metal substrate; (b) a eutectic-forming layer applied on the metal substrate and comprising a material which forms a eutectic with the metal substrate; and (c) a braze-promoting layer comprising one or more metals selected from the group comprising nickel, cobalt and iron.

BRIEF DESCRIPTION OF THE DRAWINGS

[0007] Figures 1 to 3 are photographs illustrating a brazed assembly according to a preferred embodiment of the invention.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

[0008] The present invention provides an in-situ filler metal forming material system that may eliminate the need for separately clad filler metal (or separately provided, for example as performs, etc), while maintaining a fluxless brazing method.

The present invention also provides an adjustable material braze system, so that for eg, braze fillet size or fluidity may be adjusted according to the product requirements, or on different parts of the same product, for example opposite sides of the same brazing sheet.

[0009] The inventors have also recognized that such a system can be applied to provide a range of filler metal compositions, so that both low and "high", ie normal Al-Si braze temperatures, could be achieved in a fluxless format. The ability to tailor the material system (filler metal, and braze promoters...along with braze modifiers, bonding layers, and temperature modifiers) provides significantly increased flexibility in application to aluminum alloy systems that are either not now brazeable, or not available in forms suitable for brazing. These include, for instance, high alloy content 7xxx, 2xxx, 6xxx or 8xxx series aluminum, or aluminum castings and die-castings. Specific alloys to which a Si eutectic forming layer has been applied include 3003, 5052 (2.8% Mg) and 1100 alloys. The adjustable braze response characteristics are applicable to demanding product applications, such as internal joints of heat exchangers, or brazing of intricate flow field channels formed in metal plate fuel cell engines.

[00010] The inventors have developed PVD deposition methods and layered sequence compositions, including ancillary methods to enable the practical achievement of "dry" material cleaning methods to allow preferred inline deposition processes. Successfully demonstrated dry cleaning techniques such as plasma or ion-cleaning are important steps in minimizing the environmental impact of the brazing process, and have been demonstrated to be practical as well.

[00011] The proposed fluxless brazing system begins with a substrate, which may preferably comprise an aluminum sheet material which may comprise pure aluminum, any one of a number of aluminum alloys, or a dissimilar metal coated with aluminum, eg. aluminum-coated titanium or steel. Examples of specific aluminum substrates, which can be used, are aluminum AA1100, 3003, 5xxxx, and 6xxx series aluminum alloys. In the case of 6xxx, or 5xxxx series aluminum alloys, which contain

1 or 2% or even 3% mg, the diffusion of Mg from the core into the cladding may be exploited to assist in the braze reaction, provided that a coating system using Ni as a topcoat braze promoter is employed. The small amounts of mg that can diffuse into the Si or liquid eutectic film during brazing, may assist the braze-promoting reaction of Ni in this case, since Mg itself is a braze promoter and the applicant has discovered that the use of Ni braze promoters can provide a synergistic benefit with materials containing small amounts of Mg. It is further believed that substrates containing large amounts of alloying elements, where such elements might otherwise be expected to diffuse to the surface during brazing and cause deleterious effects, can be exploited by the developed invention by depositing or providing suitable barrier coatings, which may include aluminum or ti etc. In such highly alloyed aluminum substrates, for eg high zn 7xxx, or al-li 2xxx or 8xxx alloys, a suitable low temperature filler metal system may be needed to accommodate the depressed melting temperature ranges of these alloyed materials.

[00012] In its simplest embodiment, a substrate is provided with a liquid-forming layer, preferably eutectic-forming layer, preferably comprising a coating of si. Other liquid or eutectic-forming layers may also be preferred, for example zinc, zinc-antimony, zinc-nickel, zinc-silicon, zinc-magnesium, aluminum-silicon or aluminum-zinc.

[00013] The substrate may comprise aluminum or one of the aluminum alloys mentioned above. Alternatively, depending on the composition of the eutectic-forming layer, the substrate could be comprised of one of the dissimilar metals mentioned in the applicants' co-pending application entitled "Improvements in Fluxless Brazing", filed on November 21, 2002, and incorporated herein by reference.

[00014] The Si eutectic forming layer is deposited by physical vapor deposition (pvd) in one or more steps. Here, pvd is understood to include either sputtering including magnetron sputtering, and also electron beam (EB) evaporation. For practical benefits such as rates of deposition, eb coating methods are preferred. Cathodic arc is another commercial PVD system, which may be suitable for certain

metals. It may be preferred to use a combination of source types, depending on the specific metal being deposited. For example, EB-evaporation is likely best for si, but this may or may not be best for Pb or Bi. However, comparatively little Pb is required, so a sputtered rate may be acceptable, and more efficient use of the pb might be possible. The ni or other metal such as Pd, likewise does not require much thickness and other source options might be possible, although eb-evap may still be preferred.

[00015] Sputtering of top layers may help to hold temperature of the sheet down and it puts less material on the chamber walls and more on the substrate. As applied, the si coating serves as a eutectic-forming layer. Preferably, the thickness of the si coating in the system of the invention will be from about 3 to about 20 microns, more preferably from about 5 to about 10 microns, when combined with the braze promoters described below. Where such braze promoters are not used, a thicker si coating may be necessary to obtain equivalent braze quality; or equivalent braze quality may be unachievable, or a brazing flux may become a necessary compensator. Similarly, in combination with other eutectic formers it may be possible to use thinner si coatings; however so far it appears that a si layer of about 1 micron should be in contact with the ni braze promoter. Brazing (fluxless) without this layer is very difficult indeed in this particular system; in an alternate system, for instance an Al-Zn, or Zn-Mg etc liquid forming system, Si may not be as important.

[00016] An extremely thin [20-50 nm] layer of braze modifier is preferably deposited at the interface of the si and the braze promoting layer. Preferred braze modifiers are selected from the group comprising bismuth, lead, lithium, antimony, magnesium, strontium and copper. Bismuth and lead are preferred where the eutectic-forming layer comprises silicon and the braze-promoting layer is nickel-based.

[00017] Too thick a layer of braze modifier may interfere with contact of ni and si. It may also be preferred to locate this layer at the interface between the aluminum substrate and the eutectic-forming layer, although it can interfere with adhesion of the eutectic forming layer to the substrate, and can cause peeling of the

coating in some cases due to heat transfer to the aluminum substrate during deposition of the si, or due to the time of exposure to the e-beam source, associated radiation from the vapor cloud, and the heat of condensation of the Si vapor on the substrate. To prevent this, it may be preferred to apply the si as a plurality of layers, with a cooling phase between the depositions of each layer. In addition, provision may be made for substrate cooling during coating, for example by contact with chilled surfaces on the back side of the sheet being coated, which is limited by thermal transfer of materials and contact time and geometry.

[00018] After formation of the silicon coating, the silicon coated aluminum sheet is provided with coatings of one or more braze promoters and optional braze modifiers. Preferred braze promoters are selected from one or more members of the group comprising nickel, cobalt, iron or palladium. More preferably, the braze-promoting layer is nickel-based and may preferably comprise pure nickel or nickel in combination with one or more alloying elements and/or impurities selected from the group comprising cobalt, iron, lead, bismuth, magnesium, lithium, antimony and thallium. Specific examples of nickel-based braze-promoting layers are nickel, nickel-bismuth, nickel-lead, nickel-cobalt, nickel-bismuth-cobalt, nickel-lead-cobalt, nickel-lead-bismuth, nickel-bismuth-antimony, etc. The preferred amounts of alloying elements may preferably be as disclosed in applicant's co-pending patent application entitled "Improvements in Fluxless Brazing", filed on November 21, 2002.

[00019] As an alternative to the above embodiment, the substrate can be coated with an al-si alloy; or sequential thin layers of al and si to create a desired composition of filler metal. Experiments suggest that an initial layer of thin aluminum or silicon, having a thickness of not more than about 1 micron, is preferred for adhesion of the Al-Si layer and also for the Si eutectic-forming layer described above. Similarly, a thin layer of silicon should be applied immediately under the pb or bi/ ni coating. A benefit of the sequential thin-layered approach is that heating and the stress build-up in the coating from the rate determining si step, is reduced. A thin layer of zinc, or an aluminum-zinc alloy, may be substituted for the 1 micron preferred Al or Si bonding layer or interlayer.

[00020] Still another method of depositing an al-si filler metal-forming material layer, is to use the pvd process to deposit a pre-alloyed al-si alloy. In this case, it may be preferable to deposit a hypereutectic composition, ie in the range 12 – 20 % si or higher, with suitable provisions made to compensate for unequal deposition rates of the 2-phase alloy. Similarly, it will be obvious that other alloy additions such as mg or cu may be added to the al-si alloy, to achieve ternary or quaternary, etc., alloy compositions. Zinc or zinc-aluminum may also be used in conjunction with the silicon coating, and the zinc may be prealloyed with antimony or magnesium.

[00021] In one embodiment of the system, an extremely thin layer of pb or bi is deposited on top of the si coating. This is followed by application of a topcoat of ni having a thickness of about 1 micron, or at least 0.25 to 0.5 microns.

[00022] In another embodiment of the system, fe or co are used to replace ni or as alloy additions to ni.

[00023] In yet another embodiment of the system, a layer of zn or al-zn is provided in addition to the si coating and the braze promoters. This additional layer may preferably be located underneath the si coating or immediately on top of it. Alternatively, the si could be pre-alloyed with zn or al-zn. The use of pb or bi and the ni layers may enhance the performance of these alloys.

[00024] In yet another embodiment, li may be added, possibly to replace or supplement the pb or bi or sb. Li may preferably be deposited in an alloyed form, such as al-li, due its extreme reactivity, and is likely present as an extremely thin al-li layer which may be located underneath the si or zn, or on top of the zn or si, but below the upper-most nickel braze promoter. If sb is deposited it may similarly be deposited as an alloy with al, or zn, or as a constituent of a zn-al alloy.

[00025] In yet another embodiment, a barrier coating may be provided to

[00020] Still another method of depositing an al-si filler metal-forming material layer, is to use the pvd process to deposit a pre-alloyed al-si alloy. In this case, it may be preferable to deposit a hypereutectic composition, ie in the range 12 – 20 % si or higher, with suitable provisions made to compensate for unequal deposition rates of the 2-phase alloy. Similarly, it will be obvious that other alloy additions such as mg or cu may be added to the al-si alloy, to achieve ternary or quaternary, etc., alloy compositions. Zinc or zinc-aluminum may also be used in conjunction with the silicon coating, and the zinc may be prealloyed with antimony or magnesium.

[00021] In one embodiment of the system, an extremely thin layer of pb or bi is deposited on top of the si coating. This is followed by application of a topcoat of ni having a thickness of about 1 micron, or at least 0.25 to 0.5 microns.

[00022] In another embodiment of the system, fe or co are used to replace ni or as alloy additions to ni.

[00023] In yet another embodiment of the system, a layer of zn or al-zn is provided in addition to the si coating and the braze promoters. This additional layer may preferably be located underneath the si coating or immediately on top of it. Alternatively, the si could be pre-alloyed with zn or al-zn. The use of pb or bi and the ni layers may enhance the performance of these alloys.

[00024] In yet another embodiment, li may be added, possibly to replace or supplement the pb or bi or sb. Li may preferably be deposited in an alloyed form, such as al-li, due its extreme reactivity, and is likely present as an extremely thin al-li layer which may be located underneath the si or zn, or on top of the zn or si, but below the upper-most nickel braze promoter. If sb is deposited it may similarly be deposited as an alloy with al, or zn, or as a constituent of a zn-al alloy.

[00025] In yet another embodiment, a barrier coating may be provided to

temporarily restrict diffusion of si or zn into the aluminum core; or to limit diffusion of undesirable core elements into the liquid filler metal. The barrier coating may comprise a thin coating of Ni, Ti, Ta, Cu, Nb, Sn, Pb, Bi or Al. Topcoats of braze promoters would be applied as above. During brazing, the barrier coating is eventually consumed so that eventual alloying with the aluminum core may occur, while permitting most of the liquid eutectic filler metal to remain liquid to effect the braze joint. Alternatively, if a barrier coating is required to prevent migration of species from the core into the liquid forming layer or vice versa, the liquid former will need to be provided with other material layers so that it can form its own liquid without access to the substrate, and a thicker or more resistant barrier coating may then be used.

[00026] EXAMPLES

[00027] EXAMPLE 1 - The method according to the invention was applied as follows:

Substrate : aa3003 plate, aa3003 tube.

Cleaning method: caustic cleaned plate (coupon), ie etch, rinse, desmut, rinse, dry.

Coating sequence:

3.4microns of Al/ 0.9 Si/3.4 Al/0.9Si/3.4Al/1.25 microns Si/0.005 Pb/1.5 microns Braze Quality Very Good (Good to excellent based on 4 samples run per test)

[00028] Purpose of this coating sequence: 1) to deposit an al-si alloy on the surface of the substrate, using a sequential layer approach. This approach reduces stress in each coating layer, and theoretically reduces reaction distance between si and al, for melting. It was found that as far as brazing goes, it does not make much

difference whether the al-si is applied in sequence, or just one layer of si in contact with the al substrate, as long as the Si layers are not too thick.

[00029] Preferably, the last layer deposited is si, then a very thin pb (or bi) layer is applied, and then ni. This is a particularly preferred embodiment. Furthermore, it is preferred that the ni be essentially in contact with the si, such that the very thin pb or bi layer does not degrade contact between the ni and si, and in fact it is speculated that the low melting bi or pb may actually improve contact during brazing.

[00030] Figure 1 illustrates the brazed plate and tube combination, at a magnification of 3-4x. The tube is 0.75" in diameter. Figure 2 illustrates a cross-section through the tube wall to plate joint, at a magnification of 38x. There is excellent wetting and fillet formation from the in-situ formed eutectic. Figure 3 illustrates a cross-section of the layered deposit, in the as-deposited condition, i.e. prior to braze. It is possible to resolve the individual layers shown in Figure 3, with Ni on the outermost (upper) surface.

[00031] EBEAM EXAMPLES

Coating of the substrates was carried out by pretreating approximately 4"x4" coupons of the target substrate through various means including (a) solvent degreasing, (b) caustic cleaning, whereby the coupon is immersed in 10% Oakite 360 etch solution for approximately 45 seconds, tap water rinsed, deoxidized in Oakite 125 for 10 seconds, tap water rinsed and dried, (c) mechanical brush cleaned with 3M 7A brushes, (d) sputtering with an inert gas in vacuum, (e) ion etching. Multilayer coatings were applied to the target surface through electron beam physical vapour deposition of variously prepared sources. The coupons were divided into four approximately equal samples and assessed through brazing.

Coating thicknesses were assessed using a deposition rate detector as well as microscopic (sem) assessment of metallurgical sections.

Braze tests were carried out to demonstrate the effectiveness of the coating on a target substrate sheet. In each test, braze quality was determined by placing the flat, cut end of an AA3003 O-temper aluminum tube [0.65" ID x 0.75" OD, cut to 0.5" length and ground flat on a 1.5" x 1.5" coupon of target substrate sheet and heating the arrangement in a preheated furnace in a flowing nitrogen atmosphere to approximately 1100°F for a dwell time of approximately 1 minute at maximum temperature. Braze quality was reported as excellent, very good, good, fair and poor based on visual attribute data such as fillet size, wetting characteristics, surface appearance, lustre, etc.

example

AA5052 sheet samples were prepared through (a) sputter cleaning and (b) mechanical brushing

followed by deposition of 16 μm silicon to the target interface, incremental deposition to the newly formed surface of 0.03 μm lead then 1 μm nickel. The coated sheet samples were subdivided into four coupons each for individual braze assessment. Both sets of coupons exhibited an excellent braze.

example

An AA3003 sheet sample was prepared through caustic etching followed by deposition of 16 μm silicon to the target interface, incremental deposition to the newly formed surface of 0.03 μm lead then 1.0 μm nickel. The coated sheet sample was subdivided into four coupons for individual braze assessment. All coupons exhibited an excellent braze.

Example

An AA3003 sheet sample was prepared through caustic etching followed by deposition of 16 μm silicon to the target interface, incremental deposition to the newly formed surface of 0.037 μm bismuth then 1.0 μm nickel. The coated sheet sample was subdivided into four coupons for individual braze assessment. Three coupons exhibited an excellent braze, while one exhibited a good braze.

Example

AA3003 sheet samples were prepared through ion etching for (a) 20 minutes, (b) 30 minutes followed by deposition of 16 μm silicon to the target interface, incremental deposition to the newly formed surface of 0.03 μm lead then 1.0 μm nickel. The coated sheet samples were subdivided into four coupons for individual braze assessment. The 20 minute etched coupons exhibited 2 excellent and 2 good brazed samples. The 30 minute etched coupons exhibited three excellent and 1 good braze.

Example

An AA3003 sheet sample was prepared through caustic etching followed by deposition of 28 μm silicon to the target interface, incremental deposition to the newly formed surface of 0.03 μm lead then 1.0 μm nickel. The coated sheet sample was subdivided into four coupons for individual braze assessment. All coupons exhibited an excellent braze.

Example

AA3003 sheet samples were prepared through caustic etching followed by deposition of 6 μm silicon to the target interface, incremental deposition to the newly formed surface of 0.03 μm lead then (a) 0.05 μm nickel on one sheet and (b) 1.0 μm nickel on the second. The coated sheet samples were subdivided into four coupons for individual braze assessment. The 0.05 μm coupons exhibited 2 excellent and 2 good brazed samples. The 1.0 μm coupons all exhibited an excellent braze.

Example

AA3003 sheet samples were prepared through caustic etching followed by deposition of 16 μm silicon to the target interface, incremental deposition to the newly formed surface of (a) no lead or nickel on the first and (b) 0.03 μm lead then 1.0 μm nickel on the second. The coated sheet samples were subdivided into four coupons for individual braze assessment. The non-lead/nickel coupons exhibited 2 good, 1 fair and 1 poor brazed sample. The lead containing sample exhibited 2 excellent and 2 good samples.

Example

AA3003 sheet samples were prepared through caustic etching followed by incremental deposition of alternating layers of aluminum and silicon as follows 2.0 Al, 1.8 Si, 4.0 Al, 1.8 Si, 4.0 Al, 1.75 Si μm to the target interface and subsequent deposition to the newly formed surface of (a) 0.05 μm nickel and (b) 0.01 μm lead then 0.5 μm nickel. The coated sheet samples were subdivided into four coupons for individual braze assessment. The non-leaded sample exhibited three fairs and a poor. The latter sample all exhibited an excellent braze.

Example

An AA3003 sheet sample was prepared through caustic etching followed by deposition of 10 μm zinc to the target interface, incremental deposition to the newly formed surface of 0.25 μm nickel. The coated sheet sample was subdivided into four coupons for individual braze assessment. All coupons exhibited fair braze.

Example

An AA3003 sheet sample was prepared through caustic etching followed by deposition of 25 μm zinc to the target interface, incremental deposition to the newly formed surface of 0.5 μm silicon and 0.25 μm nickel. The coated sheet sample was subdivided into four coupons for individual braze assessment at 1100°F. Three coupons exhibited good braze. Two coupons of the same composition was brazed at 1000°F and exhibited good braze.

An AA3003 sheet sample was prepared by a novel combination of ion cleaning with oxygen for 3 minutes followed by a 30 minute ion etch then deposition of 5 μm silicon to the target interface, incremental deposition to the newly formed surface of 0.03 μm lead then 1.0 μm nickel. The coated sheet sample was subdivided into four coupons for individual braze assessment. All coupons exhibited a very good braze.

What is claimed is:

1. A method for manufacturing an article of manufacture for use in a fluxless brazing process, comprising:
 - (a) providing a metal substrate;
 - (b) applying to the substrate a liquid-forming or eutectic-forming layer comprising a material which forms a liquid or a eutectic with the metal substrate; and
 - (c) applying to the eutectic-forming layer a braze-promoting layer comprising one or more metals selected from the group comprising nickel, cobalt and iron.
2. The method of claim 1, wherein the metal substrate is comprised of aluminum, an aluminum alloy, and the eutectic-forming layer comprises a material which forms a eutectic with aluminum.
3. The method of claim 1, wherein the material which forms a eutectic with the metal substrate is selected from the group comprising silicon, zinc, zinc-nickel, zinc-silicon, aluminum-silicon and aluminum-zinc.
4. The method of claim 1, wherein the eutectic-forming layer comprises silicon deposited by physical vapor deposition.
5. A method of brazing unclad first and second aluminum alloy shapes, at least one of the alloy shapes comprising a metal substrate, a layer of a liquid or eutectic-forming material applied to the substrate, and a layer of a braze-promoting layer on the eutectic forming material, the method comprising:
 - (a) assembling the shapes into an assembly to create contact between the shapes;

(b) heating the assembly under a vacuum or in an inert atmosphere in the absence of a brazing flux material at an elevated temperature and for a time sufficient for formation of a molten filler metal comprising a liquid or a eutectic of said metal substrate and the eutectic forming material, and melting and spreading of the molten filler metal to form a joint between the shapes; and

(c) cooling of the joined assembly.

6. A brazing product for fluxless brazing, comprising:

(a) a metal substrate;

(b) a liquid-forming or eutectic-forming layer applied on the metal substrate and comprising a material which forms a eutectic with the metal substrate; and

(c) a braze-promoting layer comprising one or more metals selected from the group comprising nickel, cobalt and iron.

Figure 1




Figure 2




Figure 3



INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 02/01762

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B23K35/00 B23K35/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B23K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 71784 A (CORUS ALUMINIUM WALZPROD GMBH ; MOOIJ JOOP NICOLAAS (NL); WIJENBERG) 30 November 2000 (2000-11-30) the whole document	1-3, 5, 6
A	EP 0 605 323 A (SHOWA ALUMINUM CORP) 6 July 1994 (1994-07-06)	
A	EP 0 595 601 A (SHOWA ALUMINUM CORP) 4 May 1994 (1994-05-04)	
A	US 3 597 658 A (RIVERA JOHN) 3 August 1971 (1971-08-03)	

☐ Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

11 April 2003

Date of mailing of the international search report

24/04/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mollet, G

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern: Application No

PCT/CA 02/01762

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0071784	A	30-11-2000	AU 4567100 A	12-12-2000
			BR 0010818 A	05-03-2002
			WO 0071784 A2	30-11-2000
			EP 1198625 A2	24-04-2002
			HU 0201857 A2	28-10-2002
			JP 2003500216 T	07-01-2003
			US 2002037425 A1	28-03-2002
			AU 3173701 A	24-09-2001
			WO 0168312 A2	20-09-2001
			EP 1265725 A1	18-12-2002
			US 2001040180 A1	15-11-2001
EP 0605323	A	06-07-1994	JP 7124786 A	16-05-1995
			AT 192374 T	15-05-2000
			AU 5275893 A	14-07-1994
			CA 2112441 A1	30-06-1994
			CN 1091685 A ,B	07-09-1994
			DE 69328542 D1	08-06-2000
			DE 69328542 T2	04-01-2001
			EP 0605323 A1	06-07-1994
			ES 2148212 T3	16-10-2000
			US 6200642 B1	13-03-2001
			JP 3356856 B2	16-12-2002
			JP 6248413 A	06-09-1994
EP 0595601	A	04-05-1994	AT 163383 T	15-03-1998
			AU 671309 B2	22-08-1996
			AU 5026393 A	12-05-1994
			CA 2102071 A1	01-05-1994
			CN 1090240 A ,B	03-08-1994
			DE 69317090 D1	02-04-1998
			DE 69317090 T2	23-07-1998
			EP 0595601 A1	04-05-1994
			ES 2115731 T3	01-07-1998
			JP 6200344 A	19-07-1994
			US 5594930 A	14-01-1997
			US 5581799 A	03-12-1996
US 3597658	A	03-08-1971	JP 50019431 B	07-07-1975